

PZT I-50

Standard notation: ПЦТ I-50

All shipments from

01.10.2020 to 01.05.2021

Chemical composition:

	Typical data ²	Specification ГОСТ 1581-96
Cement		
SO ₃ , %	2,9	≤ 3,5
Chlorine ion Cl ⁻ , %	0,02	≤ 0,1
Loss on ignition, %	0,7	≤ 5,0
Insoluble residue, %	0,2	≤ 5,0
SiO ₂ , %	20,5	NR
Al ₂ O ₃ , %	4,3	NR
Fe ₂ O ₃ , %	4,2	NR
CaO, %	62,7	NR
MgO, %	3,3	NR
Na ₂ O-equivalent, %	0,69	NR

Clinker

C ₃ S, %	62,5	NR
C ₂ S, %	15,0	NR
C ₄ AF, %	12,5	NR
C ₃ A, %	5,5	NR
MgO %	3,3	≤ 5,0

Physical properties:

Specific Surface Area (Blaine), m ² /kg	364	≥ 270
Free fluid, ml	3,6	≤ 8,7
Flowability, mm	249	≥ 200
Thickening time to 30 Bc/22°C, min	316	≥ 90
Flexural strength 48h/22°C, MPa	6,0	≥ 2,7

Safety characteristics:

Specific effective activity of natural radionuclides, Bq/kg	101	≤ 370
---	------------	-------

Average results of conformity testing in accordance with ГОСТ 310.2-76, ГОСТ 5382-91 and ГОСТ 26798.1-96

Branch Sukholozhskcement of SLK Cement, LLC
 Postal Code: 624803
 20 Kunarskaya Street, Sukhoi Log
 Sverdlovsk region, Russian Federation

Date: 26.04.2021
 Artem Maleev
 Technical assistance manager
 tech.support@slk-cement.com